

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08F 8/40, 230/02, G02B 1/04	A1	(11) International Publication Number: WO 00/55214 (43) International Publication Date: 21 September 2000 (21.09.00)
(21) International Application Number: PCT/EP00/02537 (22) International Filing Date: 16 March 2000 (16.03.00) (30) Priority Data: 9900935-9 16 March 1999 (16.03.99) SE (71) Applicant (for all designated States except US): PHARMACIA & UPJOHN GRONINGEN BV [NL/NL]; P.O. Box 901, NL-9700 AX Groningen (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): HODD, Kenneth, A. [GB/GB]; 5 Rackery Hall Mews, Rackery Lane, Caer-Estyn, Wrexham LL12 0PB (GB). DILLINGHAM, Keith, Alfred [GB/NL]; Verlengde Grachtstraat, NL-9717 GG Groningen (NL). DE GROOT, Jaqueline [NL/NL]; Slotbrug 8, NL-9351 SR Leek (NL). HATTJEMA, Henrik [NL/NL]; Bolster 25, NL-9321 AT Peize (NL). (74) Agents: FORSLUND, Niklas et al.; Pharmacia & Upjohn AB, S-112 87 Stockholm (SE).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: HYDROPHILIC MACROMOLECULAR COMPOUNDS (57) Abstract The invention relates to macromolecular hydrophilic photocrosslinkers having polymeric backbones of substituted ethylene groups carrying photoactive groups. The photocrosslinkers are capable of producing, when being exposed to light of determined wavelengths above 305 nm, radicals which are retained on the macromolecular photocrosslinkers and reacting so as to accomplish a crosslinked network structure. The invention further relates to the preparation of photocrosslinkers, their use in different aqueous systems and their utility in production of medical devices including ophthalmic lenses.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Hydrophilic Macromolecular compounds

Field of invention

5

The present invention relates to photocrosslinkers providing a combination of photoinitiating and crosslinking processes capable acting in an aqueous environment and being activated by visible light.

10 Background of invention

15

The UV curing of resin formulations is widely used in industry as the setting process for coatings, adhesives, and more recently paints. Such formulations may comprise a combination of vinyl, usually acrylate, monomers and crosslinkers, together with a photoinitiator. Other possible constituents of the formulations include crosslinkers and vehicles. In general an advantage of photocurable formulations is that the monomers act as their own vehicle, and the use of solvent is obviated, which has environmental advantages.

20

Advances in the technology of photocuring, improvements such as, those in UV lamps, cationic initiators for epoxide-based formulations, water borne coatings, and many novel monomers has enabled this production process to penetrate a number of important manufacturing sectors. Photopolymerization is now used in photoresists for printed circuits and microelectronics, for photolithography, magnetic recording media, glass-fiber laminates, and for medical devices, especially for dental and ophthalmic applications.

25

European Patent 0800 657 describes a photoinitiator linked to a macromer structure which together with a copolymerizable monomer and a crosslinker is capable forming a polymerization product, such as an ophthalmic lens that retains photoinitiator radical in the resulting network. This is advantageous in medical applications wherein such potentially harmful radicals must be carefully controlled. However, this system would not be applicable for producing a polymerized product directly in the capsular bag in the eye since it is not directed to photoinitiators activated by light in the visible range.

30

For the medical applications of photopolymerization it is usual to employ visible light, rather than UV, to effect the cure of the resin formulation. The use of visible, usually blue, light avoids exposing patient and dentist or surgeon to harmful irradiation. Increasingly, the merit of this approach is being recognized for industrial practice, where
5 operatives also need protection from prolonged exposure to harmful UV.

It is a characteristic of almost all, if not all, of the formulations used for aforementioned types of application that they are crosslinked. Crosslinking of the polymeric bases, which constitute the coatings, or artifacts of the aforementioned industrial products confers important advantages upon them. Crosslinked polymers have
10 greater environmental (e.g. temperature and moisture) resistance, solvent resistance and dimensional and mechanical stability, than equivalent linear polymers. This is especially so for where the equivalent linear polymer are produced by photopolymerization they have an atactic, non-crystalline, structure.

Crosslinking is introduced into photopolymerized products by including in the
15 formulation for the resin, coating or gelling system, an acrylate, or similar, crosslinker, which is characterized by having two or more crosslinkable acrylate or vinyl functions. In some formulations this crosslinking species is a polymer of low molecular weight. The crosslinker copolymerizes with the monomers of the formulation to produce a network structure.

20 It is an object of the present invention provide macromolecular compounds which act as hydrophilic photocrosslinkers for a great number of different polymeric systems provided with functional groups for crosslinking or with vinylic, acrylic and methacrylic monomers in aqueous solution and thereby retaining the photoactive radical in the crosslinked network.

25 It is another object of the present invention to provide stable hydrophilic photocrosslinkers capable of being activated at wavelengths greater than 305 nm.

It is a further object of the present invention to provide photocrosslinkers with capability to act in aqueous solutions, especially on hydrophilic polymers or water-soluble macromolecular particles made thereof having functional groups for crosslinking.

30 It is a still further object of the present invention to provide photocrosslinkers with

enhanced photoactivity (100 % conversion of monomer to polymer in aqueous solution) which reduces photoinitiator residues to a minimum, especially, vinyl modifications of the photoinitiator component and thereby reducing compositional drift, Draize and other environmental hazards.

- 5 The invention as presented below will explain how the mentioned objects are met while discussing further obvious advantages.

Description of the invention

- 10 The present invention pertains to macromolecular hydrophilic photocrosslinkers having a general formula $(A)_n(B)_m(C)_p$, wherein

(i) A, B and C are units of substituted ethylene groups in the macromolecular structure;

- 15 (ii) A, B and C are randomly distributed and the unit C carries a photoactive group;

(iii) n = 0-98 mole %, m = 0-98 mole %, n+m = 50-98 mole % and p = 0.5-50 mole %.

- When the photoactive groups of units C are exposed to light of determined wavelengths above 305 nm, radicals are generated which are retained on the macromolecular photocrosslinkers and will react to form a crosslinked network structure. Preferably the
20 final structure is solid article.

The photocrosslinker further preferably further comprises functional groups for crosslinking. Such groups are conventionally vinylic, acrylic or methacrylic groups and their nature and introduction on polymeric backbone are well known to persons skilled in the art and will be referred to as "functional groups for crosslinking".

- 25 According to one aspect of the invention an aqueous composition of the photocrosslinker in a suitable amount can be directly crosslinked into the final solid product upon sufficient irradiation. In another aspect the aqueous composition for crosslinking into a solid article comprises suitable amounts of the photocrosslinker and a hydrophilic polymer carrying functional groups for crosslinking. The photocrosslinker in
30 such a system will thereby replace the conventional combination of crosslinker and

photoinitiator. Applicable hydrophilic polymers with suitable functional can readily be provided with the skilled person for the purpose of crosslinking desired articles. For example it would be conceivable to employ polymers having a sufficiently high refractive index to be acceptable as intraocular lenses. As a further suitable example aqueous compositions of water-soluble pre-formed functionalized particles of hydrophilic polymers according to the International Patent Application PCT/EP99/04715. In a still another aspect of the present invention, the photocrosslinkers can be employed in a composition, preferably an aqueous composition further comprising at least one copolymerizable vinylic, acrylic or methacrylic monomer. Such monomers and combinations thereof are well known in the art and will not be described herein in further detail. It is, however, to be understood that the photocrosslinker will replace conventional crosslinking agents and their combination with photoinitiators in such systems.

It is highly preferred that the photoactive groups of the photocrosslinkers comprise a phosphine oxide, in order to generate the necessary radicals for crosslinking from the exposure of visible light. More preferably, the photoactive group is an acyl- or aroyl phosphine oxide.

According to a preferred aspect, the photoactive group is linked to the ethylene groups of units C of the photocrosslinkers by a linking group comprising a phenylene group. Optionally, such a phenylene group is substituted in order to obtain more stability. The photoactive group can also be linked to said the ethylene groups by means of a linking group comprising a group having the structure $-O-C(O)-NH-$, i.e. a urethane bridge. Preferably, such a linking group has a structure of $-O-C(O)-NH-Ph-$, wherein Ph denotes an optionally substituted phenylene group.

According to one embodiment of the invention, the photocrosslinkers comprises substituted ethylene units A, B, C of a macromolecular photocrosslinker in according to:

$A = -CH_2-C(R^1R^2)-$, $B = -CH_2-C(R^1R^3)-$, $C = -CH_2-C(R^1R^4)-$, wherein

R^1 is hydrogen or methyl;

R^2 is $-\text{CON}(\text{Me})_2$, $-\text{CO}_2\text{CH}_2\text{CH}_2\text{OH}$, $-\text{OCOCH}_3$, $-\text{OCOCH}_2\text{CH}_2\text{Ph}$, $-\text{OH}$ or a lactam group;

R^3 is $-\text{CON}(\text{Me})_2$, $-\text{CO}_2\text{CH}_2\text{CH}_2\text{OH}$, $-\text{OCOCH}_3$, $-\text{OCOCH}_2\text{CH}_2\text{Ph}$, $-\text{OH}$ or a lactam group when B is $-\text{CH}_2-\text{C}(\text{R}^1\text{R}^3)-$ with the proviso that R^2 and R^3 are not the same unless R^2 and R^3 is $-\text{OH}$; and

R^4 is $-\text{R}^5\text{C}(\text{O})\text{P}(\text{O})\text{R}^6\text{R}^7$ or $-\text{R}^5\text{P}(\text{O})\text{R}^6\text{OC}(\text{O})\text{R}^7$, wherein R^5 , R^6 and R^7 are selected among same or different aryl groups comprising phenyl, methylphenyl, dimethylphenyl, trimethylphenyl, methoxyphenyl, dimethoxyphenyl, trimethoxyphenyl, methylolphenyl, dimethylolphenyl, trimethylolphenyl or styryl radicals, or

R^4 is $-\text{R}^8\text{C}(\text{O})\text{P}(\text{O})\text{R}^9\text{R}^{10}$, wherein R^9 and R^{10} are the same as R^5 , R^6 and R^7 above, but R^8 is a group $-\text{O}-\text{C}(\text{O})-\text{NH}-\text{R}^{11}$, wherein R^{11} is the same as R^9 and R^{10} .

In the general formula above, $-\text{OH}$ denotes a hydroxyl group, Me a methyl group and Ph is a phenyl group. The lactam group typically is a heterocyclic ring structure of 4 to 7 atoms of which at least one is nitrogen. A suitable such lactam group provides a N-vinyl-pyrrolidone structure as one of units A or B on said ethylenic backbone. It is also to be understood that besides the mentioned substituents functional groups for crosslinking can be added to the macromolecule in accordance with conventional methods.

In one advantageous embodiment, the photocrosslinkers, R^2 and R^3 according to above are selected so as to form a water-soluble molecule.

Suitable units A and B in the general formula $(A)_n(B)_m(C)_p$ are selected among, but not limited to, N-vinylpyrrolidone (NVP), 2-hydroxyethylmethacrylate, N-N-dimethylacrylamide and vinyl acetate. The vinyl acetate referred to preferably will be hydrolyzed conventionally to vinyl alcohol. It is also referred to Table 1 below in the exemplifying part of the description for a number of specific photocrosslinkers based on such units (or co-monomers) and 4-vinylbenzoyl-diphenylphosphine oxide (VBPO) as a photoinitiating group. Accordingly, VBPO units constitute units C in said general formula above. Some especially suitable water soluble, blue light activated photocrosslinkers according to the present invention comprise NVP together with vinyl acetate units, N,N-dimethylacrylamide units alone or together with 2-hydroxyethylethacrylate units, all

combined with VBPO units. These photocrosslinkers demonstrate high conversion rate (monomer to polymer) and suitably high stability in aqueous solution. This type of photocrosslinkers can be prepared by conventional radical polymerization.

According to an alternative aspect, the units C of said general formula radical R^4 is $-O-C(O)-NH-R^8-C(O)P(O)R^9R^{10}$, wherein R^8 , R^9 and R^{10} are as above. The radical R^4 has in this context preferably been introduced by reacting isocyanate substituted photoactive compounds having the formula $O=C=N-R^8-C(O)P(O)R^9R^{10}$ with hydroxyl groups on a macromolecular backbone $(A)_m(B)_n(C)_p$, wherein units C have been selected as units A and B, as above. Typically, such a backbone comprises vinyl alcohol units derived from a monomer or copolymer of vinyl acetate, which has undergone a conventional hydrolysis step. An example of such a macromolecular backbone is a copolymer of NVP and vinyl acetate or poly(vinyl acetate).

The invention further relates to a method of forming a macromolecular crosslinked network from an aqueous composition comprising a photocrosslinker according to above, by irradiating with light exceeding a wavelength of about 305 nm for a time sufficient to form a solid article. As earlier mentioned such a composition further may comprises one or several copolymerizable vinylic, acrylic or methacrylic monomer(s), or a hydrophilic polymer provided with functional vinylic, acrylic or methacrylic groups, or combinations such monomers and polymers.

The present invention is especially useful for the production of ophthalmic lenses, particularly, where biocompatibility conferred by hydrophilic compositions is advantageous. A particularly suitable application of the inventive photocrosslinkers is to use them in the preparation of intraocular lenses produced directly in the capsular bag of the eye after surgically having removed a defect natural lens. The photocrosslinker will then be a part of an ophthalmically acceptable composition having a suitable viscosity and fluid characteristics for being injected into the eye with conventional equipment.

The photocrosslinkers according to the present invention provide for a combination of photoinitiating and crosslinking processes. It is an important feature of the present invention to effect this combination of function by attaching photoactive groups to a polymeric or macromolecular structure. The photoactive groups, when exposed to light of

the appropriate wavelength, will undergo photoinduced scission and generating radicals, which are retained on the polymeric or macromolecular structure. These retained radicals then initiate, terminate, or, in some other way participate in the gel forming process that is the objective of the radiation cure of the photomaterial. The use of the inventive

5 photocrosslinkers confers distinct advantages, both chemical and environmental, as compared with the combination of a separate photoinitiator and crosslinker. In a chemical context the use of a photocrosslinker gives opportunities to produce networks that are more homogeneous than those produced by photocuring conventional photocurable systems. The latter systems, involving as they do, combinations of monomers, have

10 structures dependent on the reactivity ratios of the monomers and crosslinkers. Often, for example, in a coating being manufactured at high rates of production, a crosslinker is selected because of its high reactivity. Disparities in the reactivities of the components of a formulation gives rise to compositional drift, the change of the average unit composition during the course of a polymerization, and this in relation to a reactive

15 crosslinker implies that sections of a network forming later, in the curing process, have a lower crosslink density than sections formed earlier. Improving the homogeneity of crosslinked networks is a subject receiving greater attention as the technical demands imposed on industrial products increases. Homogenous networks have, for example, higher fracture toughness and better optical properties heterogeneous networks. The

20 shrinkage occurring during their formation is more uniform allowing for more precision in castings. The benefits of using a photocrosslinker as a network former, as compared with a combination of photoinitiator and crosslinker, arise because the radical species they produce act as crosslinkers *via* the polymer chain to which they are attached. Further such radicals are generated throughout the setting phase, their concentration being

25 controlled by the photoinitiating species' quantum efficiency and the intensity of the light, which may be modulated during the setting, in addition to its concentration. This distinction results in the formation of networks having a more controlled and homogeneous structure.

Retaining photoinitiator residues in the network of a medical product, such as a

30 contact lens or a dental filling has desirable physiological implications. Further

photocrosslinkers because of their polymeric, or macromolecular, nature are more acceptable, environmentally, than many conventional crosslinkers which are known to cause skin and lung irritation.

Within the context of the present invention, it is possible to substitute a photocrosslinker, either completely, or partially, for a combination of a conventional photoinitiator and a conventional crosslinker. Alternatively, the inventive photocrosslinkers can be used in combination with a conventional photoinitiator or a conventional crosslinker as will be understood by practitioners skilled in formulating systems for crosslinking.

Persons skilled in this art will also appreciate that the inventive photocrosslinkers as described herein for photoactive systems responsive to visible light may be applied equally to systems responsive to UV light, so the present invention is of very general applicability.

Detailed and exemplifying description of the invention

Example 1

PHOTOCROSSLINKER POLYMER PREPARATIONS

Table 1

photocrosslink ers	VBPO (mole%) 1	Comonomer 1 (mole%)	Comonomer 2 (mole%)
P31-1	3.5	HEMA(5)	NVP(91.5)
P32-1	3.5	VAc(10)	NVP(86.5)
P40-3	4	DMA(96)	none

P40-4	4	PEMA(96)	none
P41-1	6	DMA(94)	none

The following Examples describe the preparation of P32-1(3), P40-3 & P41-1 (comparison), and P40-4 respectively. In addition examples demonstrating photocrosslinkers of DMA and 4-vinyl-2,6-dimethylbenzoylphosphine oxide are added
5 (Examples 1E and 1F).

Example 1A

Photocrosslinker Copolymer employing N-Vinylpyrrolidone and Vinyl acetate

10

This preparation, on an 8g monomer scale, used monomers in the molar ratio: 86.5 parts N-vinylpyrrolidone (VP): 10 parts vinyl acetate (Vac): 3.5 parts vinylbenzoyldiphenylphosphine oxide (VBPO).

15

Methoxydiphenylphosphine, 0.520g, was weighed to a dried 100ml twin-neck flask, with one neck septum sealed, and coated in aluminium foil to exclude light. Toluene, 3 ml, and a magnetic stir bar were added and the flask flushed with dry nitrogen. The stopcock was briefly removed and 4-vinylbenzoyl chloride, 0.409g, added, the flask being again flushed with dry nitrogen, then placed in a bath at 65°C, with magnetic stirring.

20

After 15 minutes, the other monomers: VP, 6.620g, and Vac, 0.595g, were diluted with a previously prepared solution of azobisisobutyronitrile (AIBN), 0.080g in 8ml toluene, and the mixture injected to the flask and rinsed in with a further 4ml toluene. The polymerization mixture was heated at 65°C with magnetic stirring for 8 hours, yielding a clear pale yellow solution, which was precipitated, in subdued light, to diethyl
25 ether. The supernatant was discarded and the pale sludge-like precipitate taken up in 30ml methanol and reprecipitated to ether as a curdy precipitate. The supernatant was decanted, and the polymer product dried to constant weight under vacuum at 35°C. Yield was 5.751g (72%) of friable pale yellow polymer. Elemental analysis gave 0.65%

P, corresponding to 6.9%ww VBPO units (0.209mmol/g), and 10.70% N, corresponding to 84.5%ww VP units, and thus a mean unit mass of 115 Daltons. SEC gave Mn 32,000, Mw 103,000. This implies a number average chain length of ca.280 units, with ca.7 photoactive units per chain.

5

Example 1B

Photocrosslinker Copolymer employing N-Dimethylacrylamide (I)

10 In this example, 4-vinylbenzoyldiphenylphosphine oxide (VBPO), 4 mol%, was copolymerized with N,N-dimethylacrylamide (DMA), 96 mol%, on a 6g scale.

Methoxydiphenylphosphine, 0.481g, was weighed to a dried 24x150mm Quickfit tube, and 2.5ml dry toluene added. The tube was then wrapped in aluminium foil to exclude light. 4-Vinylbenzoyl chloride, 0.368g, and a magnetic stir bar were added, and
15 the tube septum sealed, N₂ flushed, and placed in a bath at 65°C with stirring. After 15 minutes a solution of DMA, 5.26g, and AIBN, 0.060g, in toluene, 5ml, was injected by syringe and rinsed in with a further 3.6ml toluene. The mixture was stirred 6h at 65°C, yielding a viscous orange-yellow solution, which was diluted with methanol and precipitated in diethyl ether. The product was reprecipitated from methanol to ether, and
20 vacuum dessicated at room temperature. Yield, 2.56g (43%) of friable pale yellow polymer, analysis 0.82% P corresponding to 8.8%ww VBPO units (0.265mmol/g). GPC using poly(ethylene glycol) standards gave Mn 25,000; Mw 100,000.

Example 1C

25

Photocrosslinker Copolymer employing N-Dimethylacrylamide (II)

Example 2B was repeated on a 12 g scale, but with monomer ratio 6 mol% VBPO (2.12 g), 94 mol% DMA (9.89 g), with 0.120 g AIBN, 22.3 ml toluene, and polymerization
30 time extended to 8h at 65°C. The yield was 7.17g (60%) of yellow polymer, analysis

1.49% P corresponding to 16.0 %ww VBPO (0.481mmol/g).GPC gave Mn 12 000 and Mw 88000.

Example 1D

5

Photocrosslinker Copolymer employing 2-Phenylethyl methacrylate

In this example, 4-vinylbenzoyldiphenylphosphine oxide (VBPO), 4 mol%, was copolymerized with 2-phenylethyl methacrylate (PEMA), 96 mol%, on a 6g scale.

10 Methoxydiphenylphosphine, 0.271g, was weighed to a dried 24x150mm Quickfit tube, and 2.5ml dry toluene added. The tube was then wrapped in aluminium foil to exclude light. 4-Vinylbenzoyl chloride, 0.204g, and a magnetic stir bar were added, and the tube septum sealed, N₂ flushed, and placed in a bath at 65°C with stirring. After 15 minutes a solution of PEMA, 5.60g, and AIBN, 0.060g, in toluene, 5ml, was injected by
15 syringe and rinsed in with a further 3.6ml toluene. The mixture was stirred 6h at 65°C, yielding a fairly viscous pale yellow solution, which was diluted with chloroform and precipitated to methanol. The product was reprecipitated from chloroform (with THF added to clarify the solution), and vacuum dessicated at room temperature. Yield, 4.67g (78%) of friable pale yellow polymer, analysis 0.48% P corresponding to 5.2%ww VBPO
20 units (0.155mmol/g). GPC in THF using polystyrene standards gave Mn 49,300; Mw 108,500 .

Example 1E

25 In this example, 4-vinyl-2,6-dimethylbenzoyldiphenylphosphine oxide (VDMBPO), 4 mol%, was copolymerized with N,N-dimethylacrylamide (DMA), 96 mol%, on a 12g scale.

Methoxydiphenylphosphine, 0.979g, was weighed to a dried flask and 5ml dry toluene added. The flask was wrapped in aluminium foil to exclude light. 4-Viny-2,6-
30 dimethylbenzoyl chloride, 0.885g, and a magnetic stir bar were added, and the flask

septum sealed, N₂ flushed, and placed in a bath at 65°C with stirring. After 15 minutes a solution of DMA, 10.426g, and AIBN, 0.121g, in toluene, 9.3ml, was injected by syringe and rinsed in with a further 8ml toluene. The mixture was stirred 8h at 65°C, yielding a viscous pale yellow solution, which was diluted with 20ml ethanol and precipitated in diethyl ether. The product was reprecipitated from ethanol to hexane, and vacuum
5 dessicated at room temperature. Yield, 8.53g (71%) of friable pale yellow polymer, analysis 0.58% P corresponding to 6.75%ww (1.95mol%) VDMBPO units (0.187meq/g).

The polymer was water soluble and showed excellent hydrolytic stability; tested over the course of a year the product showed no measurable decrease in photoactivity.

10 GPC gave Mn 6,000; Mw 26,000 .

Example 1F

Example 1E was repeated employing VDMBPO 5 mol and DMA 95 mol%.

15 Yield was 43% of pale yellow polymer, analysis 0.86% P corresponding to 10.0%ww (2.97mol%) VDMBPO units (0.278meq/g). GPC gave Mn 7,000; Mw 32,500.

Example 1G

20 Example 1F was repeated employing VDMBPO 5 mol% and DMA 95 mol%. Yield was 55% of pale yellow polymer, analysis 0.73% P corresponding to 8.5%ww (2.49mol%) VDMBPO units (0.236meq/g). GPC gave Mn 5,600; Mw 24,000.

EXAMPLE 1H

25

1,3,5-trimethylbenzoyl-styrylphenylphosphine oxide (TMBSPO), 4 mol%, was copolymerized with N,N-dimethylacrylamide (DMA), 96 mol%, on a 12g scale.

First methoxystyrylphenylphosphine, 0.800g, was weighed to a dried flask and 5ml dry toluene added. The flask was wrapped in aluminium foil to exclude light. 1,3,5-
30 trimethylbenzoyl chloride, 1.061g, and a magnetic stir bar were added, and the flask septum sealed, N₂ flushed, and placed in a bath at 65°C with stirring. After 15 minutes

subsequently a solution of DMA, 10.241 g in 15 mL of toluene, and AIBN, 0.120 g in 5.0 mL of toluene, were injected by syringe. The mixture was stirred 8 h at 65°C, yielding a viscous pale yellow solution, which was diluted with 20 ml ethanol and precipitated in diethyl ether. The product was reprecipitated from ethanol to diethylether, and vacuum
5 dessicated at room temperature. Yield was 55% of pale yellow polymer, analysis 0.87% P corresponding to 10.4%ww (2.40mol%) TMBSPO units (0.227meq/g). GPC gave Mn 9,000; Mw 35,000.

The experiment was repeated employing TMBSPO 2.5 mol% and DMA 97.5 mol%. Yield was 79% of pale yellow polymer, analysis 0.43% P corresponding to
10 5.1%ww (1.19mol%) TMBSPO units (0.112meq/g). GPC gave Mn 15,000; Mw 94,000.

Finally, the experiment was repeated employing TMBSPO 4 mol% and PEMA 96 mol%. Yield was 68% of friable pale yellow polymer, analysis 0.56% P corresponding to 5.4%ww TMBSPO units (0.149mmol/g). GPC gave Mn 19,000 and Mw 165,000.

15 Example 11

This example illustrates the preparation of photocrosslinkers having photoactive agent linked to the ethylene backbone by a group comprising a urethane bond.

20 1 Hydrolysis of poly(*N*-vinylpyrrolidone-vinylacetate) 60:40]

For this preparation, poly(NVP-co-VAc) 60:40 (Polysciences Inc., Mw 100,000; 40 g, 0.16 mole acetate groups) was dissolved under nitrogen in methanol (200 ml) and heated to 40°C. To this solution NaOH (6.4 g, 0.16 mol) in distilled water (8.0 ml) was
25 added. After one night of reaction the solution was cooled to RT and neutralised with hydrochloric acid (33% aqueous water solution). The polymer solution was separated from precipitated salts and dialysed (Spectrapor 6 dialysis tubes, MWCO: 1000) against frequently refreshed distilled water for two days. After dialysis the polymer solution was concentrated with a rotary evaporator and diluted with methanol (150 ml). It was
30 precipitated to 1 liter of diethylether. The precipitated poly(NVP-co-VA) 60:40 was

powdered and dried over SICAPENT (Merck) for one week at 40°C in a vacuum oven connected to an oil pump, until constant weight was reached.

2 *Synthesis of 4-isocyanatobenzoyldiphenylphosphineoxide (IBPO)*

5

This reaction was performed in subdued light under an inert nitrogen atmosphere. To an oven dried threeneck flask methoxydiphenylphosphineoxide (0.177g, 6.65×10^{-4} moles) was added, followed by dry tetrahydrofuran (THF, 10 ml). The flask was wrapped in aluminium foil, to shield the reaction from outer light. The temperature was raised to 65°C. Now 4-isocyanatobenzoylchloride (Aldrich; 0.116g, 6.98×10^{-4} moles, 1.05 eq.) was added in dry THF (10 ml). After a reaction time of one hour the solvent was evaporated, and the product was retrieved as a pale yellow solid. Yield: 0.192g, 83%. Analysis with $^1\text{H-NMR}$ in $\text{DMSO-}d_6$ showed a typical pattern for the photoinitiator (PI) in the aromatic region of the spectrum, while the absorptions for the starting products had virtually vanished. This product was directly used without further purification in the next step.

3 *Synthesis of 4-isocyanato-3,5-dimethylbenzoyldiphenylphosphineoxide*

The reaction in example 2 was repeated with 4-isocyanato-3,5-dimethylbenzoylchloride instead of 4-isocyanatobenzoylchloride.



4 *Synthesis of photocrosslinker by modification of poly(NVP-co-VA) 60:40 with IBPO*

This reaction was performed in subdued light under an inert nitrogen atmosphere. To an oven dried threeneck flask 2 g of poly(NVP-co-VA) 60:40 was added and dissolved in 50 ml of dimethylacetamide (DMAA) at 40°C. Now 10 ml of DMAA was added to the reaction flask with the previous prepared IBPO, and the resulting light yellow solution was added to the poly(NVP-co-VA) 60:40 solution. After a reaction time of one night it was precipitated to diethylether (350 ml). The light yellow sticky polymer


was redissolved again in 30 ml of methanol and reprecipitated to 300 ml of diethylether. The polymer was collected over a Buchner funnel and dried for one night in a vacuum oven at 35°C. A light yellow rubbery polymer was retrieved. Yield: 1.824g (91%). With ¹H-NMR in DMSO-*d*₆ it was found that the IBDPPO had reacted with the copolymer, and its content was estimated as 2.7 mole%. It produced a crosslinked waterswellable elastic material after blue light irradiation in an experiment where it was dissolved in water together with a polymeric crosslinker.

5 *Synthesis of photocrosslinker by modification of poly(NVP-co-VA) 60:40 with*
10 *IDMBPO*


The reaction in example 4 was repeated with IDMBPO instead of IBPO. Similar yields and results could be achieved.




methoxydiphenylphosphineoxide




4-isocyanatobenzoylchloride



IBPO



4-isocyanato-3,5-dimethylbenzoylchloride



IDMBPO

Example 2

5

The following examples refer to photopolymerization including the inventive photocrosslinkers compared with photopolymerization with commercially available photoinitiators.

10

Example 2A

The state of the art photoinitiator Irgacure 1800 (ex Ciba-Geigy, 10.0 mg) was dissolved, in subdued light, in 2-hydroxyethylmethacrylate (HEMA, ophthalmic grade ex Polysciences, 970 mg) and 1,6-dihydroxyhexane diacrylate (HDDA, ex, 20.0 mg), and a 10.0 mg sample pipetted into an open DSC aluminum sample pan. The sample pan, covered with a cover-slip of thin glass, was placed in the sample position of the head of a TA Instruments Differential Photocalorimeter (DPC). The temperature of the head was allowed to stabilize under N₂ at 37°C (or in some cases 23°, and the sample irradiated with blue light at an intensity of 8-9 mWcm⁻².

20

The area of the polymerization exotherm was determined by conventional computation and the Jg⁻¹ of monomer calculated. From the Jg⁻¹ the percentage conversion of monomer to polymer was calculated using a literature value for the latent heat of polymerization of the monomer, ΔH_p. The findings are collected in Table 2.

25

Using the same composition as was used for the DPC tests discs (2mm thick x 16mm diameter) of polyHEMA were cast in PTFE casting cells. About 500mg of the mixture of monomers and photoinitiator were introduced into the cell which was closed with a glass slide and irradiated with blue light, either from a blue light dental gun, or from a

30

proprietary light generator (Efes Novacure), for 3min.

Example 2B

- 5 The method described in Example 2A was repeated using with the state of the art photoinitiator Lucirin TPO (ex BASF, 10.0mg) instead of Irgacure 1800.

Example 2C

- 10 The method described in Example 2A was repeated using HEMA (900.0mg), no HDDA, and, instead of Irgacure 1800, a photocrosslinker according to the present invention (P31-1, see Table 1. for composition, 100.0mg)

Example 2D

- 15 The method described in *Example 2C* was repeated using a photocrosslinker according to the present invention (P32-1, see Table 1. for composition, 100.0mg).

Example 2E

- 20 The method described in *Example 2C* was repeated using a photocrosslinker according to the present invention (P40-3, see Table 1. for composition, 100.0mg).

Example 2F

- 25 The method described in *Example 2C* was repeated using a photocrosslinker according to the present invention (P41-1, see Table 1. for composition, 100.0mg).

Example 2G

- 30

The method described in *Example 2A* was repeated using a photocrosslinker according to the present invention (P32-1, 100.0mg) instead of Irgacure 1800, HEMA (600.0mg), water(300mg) and no HDDA.

5 **Example 2H**

As *Example 2G*, using P40-3 (50.0mg) to replace P32-1, and HEMA (500.0mg), water (450.0mg).

10 **Example 2I**

As *Example 2H* using P41-1(50.0mg) to replace P40-3.

Example 2J

15

The method described in *Example 2A* was repeated using 2-phenylethylacrylate (PEA, 990.0mg, ex Polymer & Dajac Laboratories) instead of HEMA and no HDDA.

Example 2K

20

The method described in *Example 2A* was repeated using instead of Irgacure 1800 a photocrosslinker (P40-4, see Table 1. for composition, 100.0mg) and PEA (900mg) but no HDDA or HEMA.

25 The % conversions of monomer to polymer in Table 2., Examples 2A and 2B, the commercial photoinitiators, and the photocrosslinkers, Examples 2C to 2E, are comparable showing that the photocrosslinkers behave as efficient photoinitiators, especially giving regard to the concentrations of photoactive species, the acylphosphine oxide (shown in Table 1) Further when these findings are compared with Examples 2G to
30 2I the comparison reveals that correctly designed photocrosslinkers (Examples 2H and

2I) exhibit 100% conversions in solution in water.

For the 2-phenylethylacrylate monomer the photocrosslinker P40-4, based on 2-phenylethylmethacrylate, is also very efficient as a photoinitiator (comparing Examples 2J and 2K) giving 100% conversion of monomer to polymer gel, as judged from the heat of polymerization (based on experimentally determined ΔH_p).

Table 2. A comparison of the completeness of blue light photopolymerisation of HEMA, HEMA in water, & PEA using low molecular weight photoinitiators and photocrosslinkers

Ex. No.	Formulation ^a (wt%)[m.eq photoactive ingredient ^b /100g]	Heat of Polym. (Jg ⁻¹)	Polym. time (min)	Conversion %
2A	HEMA(97)HDDA(2)I1800(1)[0.51]]	351	3.5	80
2B	HEMA(97)HDDA(2)TPO(1)[2.9]	357	1.5	82
2C	HEMA(90)P31-1(10)[2.0]	308	6	70
2D	HEMA(90)P32-1(10)[2.3]	309	3	71
2E	HEMA(90)P40-3(10)[2.7]	307	2	70
2F	HEMA(90)P41-1(10)[4.8]	361	1.5	82
2G	HEMA(60)H ₂ O(30)P32-1(10)[2.3]	>275	>7	>63
2H	HEMA(50)H ₂ O(45)P40-3(5)[1.4]	452	7	100(approx.)
2I	HEMA(50)H ₂ O(45)P41-1(5)[2.4]	454	6	100(approx.)
2J	PEA(99)I1800(1)[0.51]	455	2.5	100(approx.)
2K	PEA(90)P40-4(10)[1.6]	456	3.5	100(approx.)

^aPhotocrosslinkers, and monomer HEMA, as Table 1.: commercial photoinitiators I1800, bis(2,6-dimethoxybenzoyl)-trimethylpentylphosphine oxide (25%) + 1-hydroxy-cyclohexylphenylketone (75%)(Irgacure 1800 ex Ciba-Geigy)

- 5 TPO, 1,3,5-trimethylbenzoyldiphenylphosphine oxide (Lucirin TPO ex BASF):
monomer PEA, 2-phenylethylacrylate: crosslinker HDDA, hexan-1,6-diol diacrylate
^bm.eq. of acylphosphine oxide/100g of formulation.

Example 3

10

Examples for Gelation Tests:

Examples 3A and 3B

- 15 Using the formulations described above in Examples 2J and 2K and the casting method described in *Example 2A* discs were prepared.

Example 3C

- 20 Irgacure 2959 (ex Ciba-Geigy, 10.0 mg) was dissolved, in subdued lighting, in 2-hydroxyethylmethacrylate (HEMA, ophthalmic grade ex Polysciences, 550.0 mg) and water (440.0 mg). Test discs (2mm thick x 16mm diameter) of polymer were cast in PTFE casting cells. About 800mg of the mixture of monomers and photoinitiator were introduced into the cell which was closed with a glass slide and irradiated with light from
25 a proprietary light generator (Efes Novacure), for 3 min.

Example 3D

As *Example 3C* with Irgacure 2959 (30.0 mg), HEMA (540.0 mg) and water (430.0 mg).

Example 3E

As *Example 3C* with P40-3 (100.0 mg) replacing Irgacure 2959, HEMA (500.0mg), and water (400.0mg).

5

Example 3F

As *Example 3C* with P41-1 (70.0mg) replacing Irgacure 2959, HEMA (510.0mg), and water (420.0mg).

10

Example 3G

As *Example 4C* with P40-4 (50.0mg) replacing Irgacure 1800, PEA (900.0mg), and additional crosslinker, CE7-2 (2-phenylethylmethacrylate/2-hydroxy-3-acryloxypropylmethacrylate copolymer [0.9:0.1 mole ratio], 50.0mg).

15

Example 3H

As *Example 3G* with Irgacure 1800 (21.0mg) replacing P40-4, PEA (940.0mg), and crosslinker, CE7-2 (2-phenylethylmethacrylate/2-hydroxy-3-acryloxypropylmethacrylate copolymer [0.9:0.1 mole ratio], 60.0mg).

20

Example 3I

As *Example 3B* with PEA (750.0mg), and photocrosslinker, P40-4 (250.0mg).

25

In Table 3. are collected the tests made to check the gelation of the different formulations. Where a composition is gelled it does not dissolve in solvent, but swells to an extent related to its crosslink density. Uncrosslinked (sol) polymers dissolve.

30

Examples of monomers photopolymerized with conventional photoinitiators of low molecular weight, nos. 4A, 4C and 4D dissolved readily in the appropriate solvent, water for polyHEMA, and acetone for polyPEA. Example no. 4B showed an intermediate behavior and dissolved partially in acetone leaving some residual gel. Increasing the proportion of photocrosslinker to 25% (3.9m.eq. of acylphosphine oxide, Example 4I or, adding separate crosslinker, CE7-2 (Example 4G, see below) produced acetone insoluble gel.

CE7-2, a polyPEMA which is unsaturated and PEA miscible, being a copolymer of 2-phenylethylmethacrylate/2-hydroxy-3-acryloxypropylmethacrylate [0.9:0.1 mole ratio], was employed as a supplementary crosslinker to the photocrosslinker P40-4, in Examples 4G and 4H. That CE7-2 is an effective cross-linker for photopolymerized PEA is demonstrated in example no. 4H, where in combination with Irgacure 1800 it also yields a gelled product upon irradiation. The products upon irradiation are transparent gelled elastomers of high refractive index ($RI > 1.54$), similar in properties to PEA/PEMA copolymers.

Examples 3E and 3F which used photocrosslinkers to replace conventional photoinitiators for HEMA/water compositions were gelled and did not dissolve in water, unlike examples 4D and 4E.

Table 3. Gelation tests on photopolymerized materials, shewing effect of photocrosslinkers

Ex. No.	Formulation (wt%) ¹	Effect of Solvent	Comments
3A	PEA(99)I1800(1)	Dissolves in Acetone	Not Crosslinked
3B	PEA(90)P40-4(10)	Dissolves & Swells in Acetone	Lightly Crosslinked
3C	HEMA(55)H ₂ O(44)I2959 ² (1)	Dissolves in Water	Not Crosslinked

3D	HEMA(54)H ₂ O(43)I2959(3)	Dissolves in Water	Not Crosslinked
3E	HEMA(50)H ₂ O(40)P40-3(10)	Swells in Water	Crosslinked Gel
3F	HEMA(51)H ₂ O(42)P41-1(7)	Swells in Water	Crosslinked Gel
3G	PEA(90)CE7-2(5)P40-4(5)	Swells in Acetone	Crosslinked Gel
3H	PEA(94)CE7-2(6)I1800(2.1)	Swells in Acetone	Crosslinked Gel
3I	PEA(75)P40-4(25)	Swells in Acetone	Crosslinked Gel

¹ See Tables 1. & 2., and text for an explanation of materials codes

²I2959, 2-hydroxy-4'-hydroxyethoxy-2-propiofenone (UV curing)

- 5 The crosslinked structure of the water swollen hydrogels (4E and 4F) was confirmed by stress relaxation tests.

Example 4

- 10 The method described in Example 2A was repeated using the following formulations:

Formulations (wt %)

- 4A. water (80)/photocrosslinker according Example 1F(20)
 4B. water (80)/photocrosslinker according Example 1H(20)
 15 4C. HEMA(45)/water(35)/photocrosslinker according to Example 1C(20)
 4D. HEMA(45)/water(35)/photocrosslinker according to Example 1F(20)
 4E. HEMA(45)/water(35)/photocrosslinker according Example 1H(20)
 4F. HEMA(45)/H₂O(35)

- 20 The coherent and clear gels resulted from the irradiation of the formulations with blue light, and their relative crosslinked nature was characterized in two ways. The first method was to measure the stress relaxation of the networks, using a Rheometrics RDA-11, and the second method used was to measure the swelling of the gels in water.

Stress Relaxation Tests-Method

The RDA-11 was set up with the 16mm gelled sample damped between parallel plates of 25 mm, heated to 35°C, and a strain of 30% applied. During the test the instrument measures the instantaneous stress necessary to maintain 35%, and plots the instantaneous shear modulus (G_i) against $\log t$. In Table 3, the percentage reductions in the modulus G_i for the formulations 4A to 4F between $i = 10$ and 100 s are compared as $(G(10) - G(100)/G(10)) \times 100$ both before and after swelling in water. The results confirm that the photocrosslinked gel possess coherent network structures.

Table 3. Average Stress Relaxations of Photocrosslinked Formulations 4A to 4F, measured at 35°C

Average stress relaxation	4A	4B	4C	4D	4E	4F
Before swelling-disc1	No result		4.9	3.4	No result	Not measurable
Before swelling-disc2	9.3		15.5	10.9	29.4	
After swelling-disc1			21.4	17.4		
After swelling-disc2	19.1		19.0	13.0	12.4	Not measurable

Swelling Test Method

Samples discs from formulations 4A through 4F were weighed, immersed in water for 24 hours at 20°C, dried, and reweighed. Table 4 compares the water absorbed by each formulation on a percentage basis.

Table 4.


Percentage water absorbed at 25°C by photocrosslinked gels

Water absorbed (wt %)	4A	4B	4C	4D	4E	4F
Disc1			222	191		Not measurable
Disc2	130	219	230	172	255	Not measurable

- 5 It was observed that upon irradiation with blue light, the formulation prepared without a crosslinker (4F) did not gel and that no discs suitable for any measurements were formed. Satisfactory discs were prepared from other formulations and stress relaxation results and the water absorption results were in agreement with the sequence: most highly crosslinked 4A>4C<4E least highly crosslinked.

Claims

1. Macromolecular hydrophilic photocrosslinkers having a general formula



capable of producing, upon exposure to light, crosslinked networks, wherein

- 10 (i) A, B and C are units of substituted ethylene groups in the macromolecular structure;
- (ii) A, B and C are randomly distributed and the unit C carries a photoactive group;
- (iii) $n = 0-98$ mole %, $m = 0-98$ mole %, $n+m = 50-98$ mole % and $p = 0.5-50$ mole %;

15 and when said photoactive groups are exposed to light of determined wavelengths above 305 nm, radicals are generated and retained on the macromolecular photocrosslinkers and reacting so as to accomplish a crosslinked network structure.

20 2. Photocrosslinkers according to claim 1 characterized in that said photoactive group comprises a phosphine oxide.

3. Photocrosslinkers according to claim 2 characterized in that the photoactive group is an acyl- or aroyl phosphine oxide.

25 4. Photocrosslinkers according to claim 3 characterized in that the photoactive group is linked to the ethylene groups of units C by a linking group comprising a phenylene group, said phenylene group being optionally substituted.

30 5. Photocrosslinkers according to claim 3 characterized in that the photoactive group is linked to the ethylene groups of units C by a linking group comprising a group having the structure

-O-C(O)-NH-

6. Photocrosslinkers according to claim 5, wherein the linking group has the structure of -O-C(O)-NH-Ph-, wherein Ph denotes an optionally substituted phenylene group.

5

7. Photocrosslinkers according to claim 1, wherein the ethylene units A, B, C of the macromolecular structure comprises substituents in accordance with:

A = -CH₂-C(R¹R²)-, B = -CH₂-C(R¹R³)-, C = -CH₂-C(R¹R⁴)-, wherein

10

R¹ is hydrogen or methyl;

R² is -CON(Me)₂, -CO₂CH₂CH₂OH, -OCOCH₃, -OCOCH₂CH₂Ph, -OH or a lactam group;

15

R³ is -CON(Me)₂, -CO₂CH₂CH₂OH, -OCOCH₃, -OCOCH₂CH₂Ph, -OH or a lactam group when B is -CH₂-C(R¹R³)- with the proviso that R² and R³ are not the same unless R² and R³ is -OH; and

R⁴ is -R⁵C(O)P(O)R⁶R⁷ or -R⁵P(O)R⁶OC(O)R⁷, wherein R⁵, R⁶ and R⁷ are selected

20

among same or different aryl groups comprising phenyl, methylphenyl, dimethylphenyl, trimethylphenyl, methoxyphenyl, dimethoxyphenyl, trimethoxyphenyl, methylolphenyl, dimethylolphenyl, trimethylolphenyl or styryl radicals, or

R⁴ is -R⁸C(O)P(O)R⁹R¹⁰, wherein R⁹ and R¹⁰ are the same as R⁵, R⁶ and R⁷ above, but R⁸ is a group -O-C(O)-NH-R¹¹, wherein R¹¹ is the same as R⁹ and R¹⁰.

25

8. Photocrosslinkers according to claim 7, wherein R² and R³ are selected so as to form a water-soluble molecule.

9. Photocrosslinkers according to claim 7, wherein said lactam units together with units A or B constitute N-vinylpyrrolidone units.

30

10. Photocrosslinkers according to claim 7, wherein at least one of R^2 and R^3 is hydroxyl.

11. Photocrosslinkers according to claim 7, wherein A is N-vinylpyrrolidone, B is vinyl
5 alcohol.

12. Photocrosslinkers according to claim 7, wherein R^4 is $-O-C(O)-NH-R^8-C(O)P(O)R^9R^{10}$.

13. Photocrosslinkers according to claim 1 or 7 provided with functional groups for
10 crosslinking.

14. Photocrosslinkers according to claim 13 provided with functional groups selected
among vinylic, acrylic and methacrylic groups.

15. A method of preparing a photocrosslinker from a hydrophilic macromolecule
 $(A)_n(B)_m(C)_p$

(i) A, B and C are units of substituted ethylene groups in the macromolecular
structure;

(ii) A, B and C are randomly distributed and at least the unit C carries a hydroxyl
20 group;

(iii) $n = 0-98$ mole %, $m = 0-98$ mole %, $n+m = 50-98$ mole % and $p = 0.5-50$ mole %;

by reacting said macromolecule with an isocyanate substituted photoactive agent having
the structure $-C(O)=N-R^8-C(O)P(O)R^9R^{10}$, wherein R^8 , R^9 and R^{10} are selected among
25 same or different aryl groups comprising phenyl, methylphenyl, dimethylphenyl,
trimethylphenyl, methoxyphenyl, dimethoxyphenyl, trimethoxyphenyl, methylolphenyl,
dimethylolphenyl, trimethylolphenyl or styryl radicals.

16. A method of forming a macromolecular crosslinked network from an aqueous
30 composition comprising a photocrosslinker according to any of claims 1 to 14 by

irradiating with light exceeding a wavelength of about 305 nm for a time sufficient to form a solid article.

17. A method according to claim 16, wherein said composition further comprises at least one copolymerizable vinylic, acrylic or methacrylic monomer.

18. A method according to claim 16, wherein said composition further comprises a hydrophilic polymer provided with functional vinylic, acrylic or methacrylic groups.

19. A method according to claim 18, wherein said hydrophilic polymer forms discrete crosslinkable units in form of water-soluble particles.

20. A method according to any of claims 16 to 19, wherein an ophthalmic lens is produced from said composition.

21. A method according to any of claim 20, comprising the steps of injecting said composition into the capsular bag of the eye and crosslinking it into a final lens product by irradiation of a wavelength exceeding 305 nm.

23. An ophthalmically acceptable composition comprising the photocrosslinkers according to any of claims 1 to 15 having a refractive index of at least 1.39 and a suitable viscosity to be injected through a standard cannula of 15 Gauge, or finer.

24. The use of photocrosslinkers according to any of claims 1 to 15 in an ophthalmically acceptable composition for injection into the capsular bag of the eye.

INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/EP 00/02537

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F8/40 C08F230/02 G02B1/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	L. ANGIOLINI: "POLYMERIC PHOTOINITIATORS BEARING SIDE-CHAIN BENZOYLDIPHENYLPHOSPHINOXIDE MOIETIES FOR UV CURABLE COATINGS." JOURNAL OF APPLIED POLYMER SCIENCE, vol. 51, no. 1, 3 January 1994 (1994-01-03), pages 133-143, XP000464122 NEW YORK, US page 133 -page 143	1-19
Y	WO 92 09644 A (BAUSCH & LOMB INC.) 11 June 1992 (1992-06-11) page 6, line 1 - line 21; claims 1-30	1-24
Y	WO 92 07885 A (BIOCOMPATIBLES LTD.) 14 May 1992 (1992-05-14) claims 1-16	1-24

	---/---	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

3 July 2000

Date of mailing of the international search report

14/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Permentier, W

INTERNATIONAL SEARCH REPORT

Internat I Application No

PCT/EP 00/02537

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>WO 99 08135 A (ALCON LABORATORIES, INC.) 18 February 1999 (1999-02-18) page 4, line 5 - line 14 page 5, line 4 - line 30 page 6, line 2 - line 14 page 7, line 7 - line 21 page 7, line 32 -page 8, line 7 page 9, line 10 - line 25; claims 1-15</p>	1-24
A	<p>WO 99 08136 A (ALCON LABORATORIES, INC.) 18 February 1999 (1999-02-18) claims 1-20</p>	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat Application No

PCT/EP 00/02537

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9209644 A	11-06-1992	US 5219965 A AT 144996 T BR 9107041 A CA 2095045 A CN 1061785 A,B DE 69123059 D DE 69123059 T EP 0559809 A ES 2096067 T HK 1006464 A JP 6503373 T KR 184239 B US 5364918 A US 5525691 A	15-06-1993 15-11-1996 28-09-1993 28-05-1992 10-06-1992 12-12-1996 05-06-1997 15-09-1993 01-03-1997 26-02-1999 14-04-1994 15-05-1999 15-11-1994 11-06-1996
WO 9207885 A	14-05-1992	AT 146488 T DE 69123756 D DE 69123756 T DK 555295 T EP 0555295 A ES 2094824 T GR 3022397 T HK 53297 A JP 3009356 B JP 9020814 A JP 2593993 B JP 6502200 T SG 43188 A	15-01-1997 30-01-1997 03-04-1997 16-06-1997 18-08-1993 01-02-1997 30-04-1997 02-05-1997 14-02-2000 21-01-1997 26-03-1997 10-03-1994 17-10-1997
WO 9908135 A	18-02-1999	US 6015842 A AU 8396398 A EP 1002243 A	18-01-2000 01-03-1999 24-05-2000
WO 9908136 A	18-02-1999	US 5891931 A AU 8396498 A CN 1251174 T EP 1002244 A	06-04-1999 01-03-1999 19-04-2000 24-05-2000